



VISCOWAX® P51G

PP-Wax

CAS Number: 9003-07-0

VISCOWAX® P51G – high quality polypropylene wax

Characteristics	Reference Value	Units	Test Method
Viscosity @ 170 °C *	50-100	mPas	DGF M-III 8
Drop Point *	150-160	°C	DGF M-III 3
Solidification Point	106-110	°C	DGF M-III 4a
Needle Penetration	< 2	10 ⁻¹ mm	DGF M-III 9b
Type of delivery	Granules	-	Visual
Appearance	White	-	Visual

* general supply specification

DGF: Test methods of the Deutsche Gesellschaft für Fettwissenschaft e.V. Münster i.W.

VISCOWAX® P51G can be used in many different applications. Please contact us to get more information about the special properties of our product and the potential use / advantage in your application.

Main scope of applications and effects:

- **Carrier material and dispersing aid in pigment and additive concentrations / Masterbatches**
- **Lubricant for PVC processing**
- **Processing agent for PP**
- **Additive for hot melt adhesives**



VISCOWAX® P51G

PP-Wax

Status under Food Legislation

EU: Listed in Annex I of Regulation (EU) 10/2011

For further information please contact us under the below mentioned address.

Safety and Environment

VISCOWAX® P51G has not been classified as hazardous materials in accordance with the Regulation (EC) No. 1272/2008 (CLP/GHS) and therefore it does not require marking.

Please refer to our Safety Data Sheet for further safety relevant information.

Form of Delivery, Packaging and Storage

VISCOWAX® P51G is shipped as granules either in multilayer paper bags or PE bags of 25 kg net. The product is palletised (preferably 750 kg net) on CP2-pallets (1200mm x 800mm) which are shrink-wrapped.

Big bags of different sizes up to 1000kg net palletised on CP3-pallets (1140mm x 1140mm) are also available.

The product shall be stored in its original packaging at room temperature in a dry place. Avoid direct sun radiation and water contact.

Please do not hesitate to contact us for further details.

Innospec Leuna GmbH
Am Haupttor, Bau 6310
D-06237 Leuna, Germany
Tel.: +49(0)3461-434065
Fax : +49(0)3461-434070
E-mail: leuna@innospecinc.com
www.innospecinc.com

Leuna, October 2018

The general points listed correspond to our current knowledge and have been elaborated to the best of our belief and under consideration of professional care. Herewith, we do not guarantee definite properties nor suitability for a particular application. It is the customer's duty to particularly check suitability of the product for the use intended.